



 Research Article

REASONABLE USE OF HEAT AND HEAT CONDUCTIVITY PROPERTIES OF HEAT PRESERVING COATINGS

Submission Date: March 18, 2024, **Accepted Date:** March 23, 2024,

Published Date: March 28, 2024

Crossref doi: <https://doi.org/10.37547/ijasr-04-03-19>

Journal Website:
<http://sciencebring.com/index.php/ijasr>

Copyright: Original content from this work may be used under the terms of the creative commons attributes 4.0 licence.

Boburjon Tojiboyev

Lecturer, Fergana Polytechnic Institute, Fergana, Uzbekistan

Maftuna Mullajonova

Assistant, Fergana Polytechnic Institute, Fergana, Uzbekistan

ABSTRACT

In addition to discussing the current techniques for figuring out the thermal conductivity of these heat-insulating coatings, the piece also details the outcomes of experimental research on the analysis and advancement of energy-saving materials and their application to recently built modern buildings and structures.

KEYWORDS

Energy efficiency, heat insulating material, thermal conductivity, microsphere, heat insulating paint, thermocouple sensors.

INTRODUCTION

By the 21st century, saving and rationally using heat in housing and communal facilities, heat-operated plants and factories remains an important and priority task. With higher energy prices and improved market conditions for mechanical insulation products, designers and

plant owners are increasingly interested in using them to reduce energy consumption by improving energy efficiency.

The main part

Insulation is a material or set of materials used to resist heat flow.

A coating is a liquid or semi-liquid material suitable for application to thermal insulation or other surfaces that dries or hardens to form a protective coating and is 30 mils (0.76 mm) or less thick per layer.

Combining the two definitions, it is considered that "thermal insulation" does not include thermal insulation, but can be used as thermal insulation by itself.

We know that there are heat losses in pipes when hot water comes from heat sources to the population. We can see this in Figure 1 below



Figure 1. Factors causing loss of hot water from heat sources to the population

The heat-retaining coating that we are researching is distinguished by its comprehensive convenience and compliance with the requirements for heat-insulating coatings.

Heat-insulating coating is an innovative energy-saving material, a polymer-based composition consisting of hollow ceramic microspheres.

It is advisable to use this coating in the construction industry instead of the usual heat-retaining (glass) materials.

Advantages:

Flame retardant (does not burn)

Resistant to acids and alkalis

It is easy to apply (it can be done by spraying with a brush, roller and compressor);

Forms a very compact layer;

Not harmful to human health;

Does not harm nature;

Contains no harmful substances;

Fields of application

By applying it to valves and valves, it allows to preserve heat (usually glass is not wrapped in valves and valves);

Heat is saved by applying it to industrial containers;

Protects against noise and decay by spraying into vehicle cabins;

Residential and industrial buildings (saves heat, prevents mold and adds beauty to the city appearance by applying it to the exterior and interior);

It is very easy to apply, spray and coat;

Metal constructions (coolness in summer keeps heat in winter);

Heating mains, pipes, ventilation ducts;

The scope of application of heat-retaining coating is really impressive. Let's take a closer look at examples of the use of material for different types of surfaces.

Application of coating for the exterior of the building:

Widely used as a facade. This material has increased elasticity, so microcracks do not form on it even with sudden changes in temperature. Depending on the thickness of the layer, the heat-retaining coating reduces heat loss by up to 30%, which allows to increase the temperature in the room by 4-6 °C in the cold season. In summer, on the contrary, the coolness remains.

Application of coating for wooden walls:

Thermal insulation of wooden houses with mineral wool or foam can significantly reduce the aesthetic properties of the building, but the application of the coating we offer is one of the best solutions for wooden houses, not only insulating the house, but also it allows to emphasize the decorative properties of wood. The composition includes antibacterial substances that eliminate the risk of parasites, mold, pathogenic microbes. Due to its excellent fire-resistant properties, the paint protects the material from possible fires.

The coating can be applied to brick, wood, metal, concrete, plastic and many other surfaces. The surface is pre-cleaned, if necessary, it is cleaned with special chemicals, the same composition is diluted with water (no more than 5%) or any acrylic paint, liquid glass mixture can be used as a primer.

The coating cannot be applied to wet, icy surfaces. The coating is laid in several layers. The number of layers is determined depending on the tasks and goals. It can be applied several times between drying layers. The final thickness of the finished coating is selected depending on the temperature of the heat carrier and the desired surface temperature.

The coating is easily sprayed (laid) on the surface of any geometric shape using a brush, spatula, roller or sprayer. The coating does not release harmful compounds into the atmosphere. A regular respirator is recommended when working in a non-ventilated building, a respirator is not necessary when working outdoors or in a

ventilated room. Average consumption for obtaining a dry coating layer 1 mm thick: 750-1000 g/m².

My pen has the following features:

- low density. Bulk density - 0.35-0.6 g/cm³. The density of the material

particle walls - 2.4-2.5 g/cm³. Particle size is 10-500 microns. The thickness of the sphere shell is - 10% of the diameter.

- high fluidity. Due to the shape of the particles, the microspheres have increased fluidity, providing good fluidity as a free-flowing material.

filling out forms.

- low thermal conductivity. Thermal conductivity of microspheres 0.06-0.08 W/m °C at 20 °C.

- strength. Microspheres are 3-10 times stronger than most hollow glass spheres. Unlike glass spheres, microspheres have a higher compressive strength due to their stronger shell. Compressive strength - 15-30 MPa.

- inactivity. Due to their chemical composition, microspheres are resistant to solvents, organic solutions, water, acids or alkalies without losing their properties.

- heat resistance. Microspheres do not lose their properties at temperatures above 1000 °C. The melting temperature is not lower than 1200 °C.




Figure 2. Microsphere

In order to "warm up" all its parts and make the transfer of heat flow stationary, in order to stabilize the indicators of the equipment, the

indicators of all three thermocouple sensors were measured for 0.5 hours at 5-minute intervals.

To calculate the individual error of the thermocouple sensors, before the start of the experiments, the temperature of each sensor immersed in a Dewar container filled with melted ice was measured, and the temperature deviation from 0°C was taken into account during the experiments.

Initially, testing was carried out to determine the reliability of the equipment for measuring the thermal conductivity of heat-insulating paint.

REFERENCES

1. Qo'chqarov, B. U., Tojiboyev, B. T., & Axtambayev, S. S. (2021). Experimental determination of the gas consumption sent to the device for wet dusting in the humid mode. *Экономика и социум*, (6-1), 226-229.
2. Маткаримов, Ш. А., Зияев, А. Т., Тожибоев, Б. Т., & Кучкаров, Б. У. (2020). Покрытие задвижек и запорной арматуры тепловых сетей жидким теплоизоляционным покрытием. *Universum: технические науки*, (12-5 (81)).
3. Boburjon Tolibjonovich Tojiboyev (2021). Heat resistant fluid insulating coat. *Scientific progress*, 2 (7), 524-531.
4. Эргашев Насимбек Ахмаджонович, Маткаримов Шухрат Адхамович, Зияев Абдукарим Ташпулатович, Тожибоев Бобир Толибжонович, & Кучкаров Бобирмирзо Улугбекович (2019). Опытное определение расхода газа, подаваемое на пылеочищающую установку с контактным элементом, работающим в режиме спутникового вихря. *Universum: технические науки*, (12-1 (69)), 29-31.
5. Халилов, Ш. З., Тожибоев, Б. Т., Умаров, Э. С., & Кучкаров, Б. У. (2019). Прием и хранение зерновой смеси, поступающей после комбайнов. *Журнал Технических исследований*, (2).
6. Tojiev, R., Ortikaliyev, B., & Tojiboyev, B. (2019). Improving selecting technology of raw materials of fireproof bricks. *Тенденции и перспективы развития науки и образования в условиях глобализации. Украина*, 27(46), 606-609.
7. Tojiboyev, B. T. (2020). Euphemism and gender: linguocultural euphemisms among males and females in uzbek and english language. *International journal of discourse on innovation, integration and education*, 1(5), 8-11.
8. Халилов, Ш. З., Тожибоев, Б. Т., & Кучкаров, Б. У. (2020). Причина скачков при трении. *Журнал Технических исследований*, 3(1).
9. Tojiboyev, B. T., & Mo, A. A. O. G. L. (2021). Liquid composition heat insulating coats and methods for determination of their heat conductivity. *Scientific progress*, 2(6), 1628-1634.
10. Tojiboyev, B. T., & Alijon o'g'li, M. B. (2020). Some questions of suffixation, impact and alternation by the background in borrowed words with the value of a face in russian. *International journal of discourse on innovation, integration and education*, 1(5), 71-77.
11. Tojiboyev, B. T., & Gapporov, Q. G. ugli Raxmonov, AT (2020). Reception and Storage

- of Grain Mixture Generated After the Combines. International Journal of Engineering and Information Systems (IJEAIS). www.ijeais.org/ijeais, ISSN, 96-100.
12. Мирзаходжаев, Ш. Ш., Тожибоев, Б. Т., & Ахмедов, Р. Р. (2019). Характеристика опытного образца комбинированного фронтального плуга с активными рабочими органами. In концепции устойчивого развития науки в современных условиях (pp. 46-48).
13. Toshpo'latovich, Z. A., & Tolibjonovich, T. B. (2021). Calculation of Thermal State of Sleeves and Cylinder Covers. Central asian journal of theoretical & applied sciences, 2(11), 229-236.
14. Boburjon Tolibjonovich Tojiboyev (2021). Heat resistant fluid insulating coat. Scientific progress, 2 (7), 524-531.
15. Tojiboyev, Bobur Tolibjonovich , & Yusupova, Nafisaxon Xursanaliyevna (2021). Suyuq kompozitsion issiqlik izolyatsiyalovchi qoplamalari va ularning issiqlik o'tkazuvchanlik koeffitsientini aniqlash usullari. Oriental renaissance: Innovative, educational, natural and social sciences, 1 (10), 517-526.
16. Akramova, N. M., & Dekhkonboy, N. O. (2019). Phraseological euphemisms in modern English. Проблемы современной науки и образования, (12-2), 110-112.
17. Akramova, N. M. (2019). Dekhkonboy Nabirasi O. Phraseological euphemisms in modern English. Problemy Nauki, (12-2), 145.
18. Tojiboyev, B. T. (2020). Euphemism and gender: linguocultural euphemisms among males and females in uzbek and english language. International journal of discourse on innovation, integration and education, 1(5), 8-11.
19. Dekhkonboy Nabirasi Omongul Makhamadsoli Qizi (2020). Euphemisms dedicated to the theme of animals in the English and Uzbek languages. Вестник науки и образования, (10-3 (88)), 49-51.
20. Kizi, D. N. O. M. (2021). Poetic use of euphemistic meaning and their sociolinguistics analysis. Academicia: an international multidisciplinary research journal, 11(2), 1124-1131.
21. Tolibjonovich, T. B. (2024). Energy-saving materials and prospects of their application to building construction. Western European Journal of Modern Experiments and Scientific Methods, 2(2), 29-33.