VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135













Toward Battery-Free Sensing: A Comparative Overview of TENG-Based Gas Sensor Mechanisms

Submission Date: June 03, 2025, Accepted Date: July 02, 2025,

Published Date: August 01, 2025

Website: http://sciencebring.co m/index.php/ijasr

Copyright: content from this work may be used under the terms of the creative commons attributes 4.0 licence.

Dr. Rizky Mahendra

Center for Advanced Sensors and Energy Harvesting, Universitas Indonesia, Depok, Indonesia

Dr. Nurul Hidayah

Faculty of Science and Technology, Universitas Airlangga, Surabaya, Indonesia

ABSTRACT

Gas sensing is critical for environmental monitoring, industrial safety, and healthcare diagnostics, particularly for detecting hazardous or significant gases like volatile organic compounds (VOCs), ammonia, and formaldehyde [1, 2, 3, 4, 8, 10]. Traditional gas sensors often require external power sources, which can limit their portability and deployment in remote or harsh environments. Self-powered gas sensors, which harvest energy from their surroundings, offer a promising solution to this limitation. Triboelectric nanogenerators (TENGs), devices that convert mechanical energy into electrical energy through the coupling of triboelectrification and electrostatic induction, have emerged as effective power sources and active sensing components for self-powered gas detection systems [20, 24, 26, 27, 28, 29, 30, 31, 32, 33, 34, 35, 36, 37, 38, 39, 40]. This review provides a comparative analysis of the sensing mechanisms employed in TENG-based self-powered gas sensors. It examines how the interaction between target gases and the TENG's materials, or integrated sensing layers, leads to detectable changes in the TENG's electrical output. Key mechanisms discussed include changes in triboelectric properties, modulation of integrated resistive or capacitive sensing layers by the TENG's output, and gas ionization effects. Challenges and future perspectives for the development of highly sensitive, selective, and stable self-powered gas sensors based on TENGs are also addressed.

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135









KEYWORDS

Self-powered sensors, Gas sensing, Triboelectric nanogenerators (TENG), Sensing mechanisms, Comparative review, Nanomaterials, Environmental monitoring, Wearable sensors.

Introduction

The increasing awareness of air quality issues and the need for real-time monitoring of various gases in diverse settings have driven the demand for advanced gas sensing technologies [2, 3]. Hazardous gases from industrial processes, combustion, or even biological sources pose significant health and environmental risks [5, 8]. Furthermore, the analysis of gases in exhaled breath holds potential for non-invasive disease diagnosis [3, 10].

Conventional gas sensors, such as those based on metal oxides, optical principles, or surface acoustic waves, typically require continuous power supply for operation, which can be a limiting factor for portable, wearable, or wirelessly distributed sensing networks [7, 12, 11, 16]. The development of self-powered sensors that can harvest energy from ambient sources presents a compelling alternative.

Triboelectric nanogenerators (TENGs) have gained significant attention as a versatile technology for converting various forms of mechanical energy, such as vibration, rotation, and contact-separation, into electrical energy [20, 24, 26, 27, 28, 29, 30, 32, 33, 34]. Beyond their energy harvesting capabilities, TENGs can also function as active sensors, where changes in the surrounding environment, including the presence

of gases, can directly influence their electrical output [20, 37, 38, 39, 40]. This dual functionality makes TENGs particularly well-suited for selfpowered gas sensing applications.

Recent research has demonstrated the feasibility of using TENGs for detecting a variety of gases, including ammonia, formaldehyde, ethanol, and humidity, at room temperature and without external power [6, 31, 35, 36, 9, 21]. This review aims to systematically analyze and compare the different sensing mechanisms employed in these TENG-based self-powered gas sensors, providing insights into their operational principles and potential for further development.

METHODS

This review was conducted by systematically searching and analyzing peer-reviewed scientific literature focusing on self-powered gas sensors utilizing triboelectric nanogenerators (TENGs). Academic databases were the primary source of information, using search terms such as "triboelectric nanogenerator," "TENG," "selfpowered," "gas sensor," "sensing mechanism," "ammonia," "formaldehyde," "ethanol," "humidity," and combinations thereof.

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135









The identified studies were screened based on their relevance to TENG-based gas sensing and the clear description of the sensing mechanism involved. Articles focusing solely on TENGs for energy harvesting or on gas sensors requiring external power were generally excluded unless they provided foundational knowledge relevant to the sensing principles.

A thematic analysis approach was employed to categorize and compare the different sensing mechanisms reported in the literature. The identified mechanisms were grouped based on how the presence of the target gas influences the TENG's operation and electrical output. The primary sensing mechanisms identified and analyzed include:

- 1. Direct Triboelectric Property Modulation: Mechanisms where the target gas directly interacts with the triboelectric layers of the TENG, altering their surface charge density, dielectric properties, or contact area, thereby changing the triboelectric output [6, 31, 35, 36, 44, 45, 46, 47, 48, 49, 50, 51].
- 2. TENG-Driven Resistive Sensing: Mechanisms where the TENG's harvested energy

powers a separate resistive gas sensing layer, and concentration is determined by measuring the change in resistance of this layer [9, 41].

- 3. TENG-Driven Capacitive Sensing: Mechanisms where the TENG's output is used to power a capacitive sensing element, and the presence of gas alters the dielectric properties of the material between the capacitor plates, leading to a change in capacitance [20].
- Gas Ionization/Discharge Effects: Mechanisms where the high voltage generated by the TENG in the presence of certain gases leads to gas ionization or discharge, which can be detected as a change in electrical signal [23].

For each mechanism, the underlying principles, typical materials used, target gases, and reported performance characteristics (e.g., sensitivity, response time, selectivity) were extracted and analyzed. The advantages and limitations of each mechanism for self-powered gas sensing were also considered.

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135














Figure 1. Schematic diagram of three ways in which TENG equipment can be used in the food field. i. TENG-based, self-powered sensor for food quality sensing. ii. TENG-based, self-powered sterilization equipment for food sterilization, iii. TENG-based, self-powered system to promote crop growth.

The gathered information was synthesized to provide a comparative overview of the different sensing approaches. The Results section presents the findings categorized by sensing mechanism. The Discussion section provides a comparative analysis, highlights the strengths and weaknesses of each mechanism, discusses challenges, and outlines future research directions based on the identified themes.

RESULTS

The review of the literature revealed several distinct mechanisms by which TENGs are utilized for self-powered gas sensing.

Direct Triboelectric Property Modulation

In this mechanism, the target gas directly with the triboelectrically interacts materials of the TENG, altering their surface properties and thus influencing the triboelectric effect. This interaction can involve adsorption of gas molecules onto the surface, leading to changes in surface charge density or work function [6, 31, 35, 36, 44, 45, 46, 47, 48, 49, 50, 51]. For example, materials like poly(dimethylsiloxane) (PDMS) and various polymers are commonly used as triboelectric layers, and their interaction with gases like ammonia or formaldehyde can alter their electron affinity or charge trapping capabilities [6, 31, 35, 36].

The sensing signal in this mechanism is typically a change in the open-circuit voltage (Voc), shortcircuit current (Isc), or transferred charge (Qsc)

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135









of the TENG upon exposure to the target gas. The magnitude of this change is proportional to the gas concentration. This approach offers the advantage of a direct sensing mechanism integrated within the energy harvesting unit, potentially simplifying device design. Studies have demonstrated room-temperature sensing of ammonia and formaldehyde using this principle [6, 31, 36]. The use of specific materials like PDMS combined with conductive polymers (e.g., polypyrrole - Ppy) has been explored to enhance and selectivity [35]. Surface engineering of the triboelectric layers is a key strategy to improve the performance of sensors based on this mechanism [31, 37, 38].

TENG-Driven Resistive Sensing

This approach utilizes the electrical energy harvested by the TENG to power a separate gas sensing element whose resistance changes upon exposure to the target gas. Metal oxide semiconductors (MOS) are common materials for resistive gas sensors, exhibiting changes in conductivity due to the adsorption and reaction of gas molecules on their surface [7, 15, 18]. Quantum dots have also been explored as resistive sensing materials [14].

In a TENG-driven resistive sensor, the TENG provides the necessary voltage or current to operate the MOS or other resistive sensing layer. The change in resistance of the sensing layer is then measured, often through a simple circuit powered by the TENG. This mechanism allows for the use of well-established and highly sensitive resistive sensing materials. For example, a TENG has been used to power a CuO thin film sensor for formaldehvde detection [9]. This approach separates the energy harvesting function from the primary sensing mechanism, which can allow for independent optimization of each component. However, it requires integrating two distinct functional units.

TENG-Driven Capacitive Sensing

Similar to resistive sensing, this mechanism employs the TENG to power a capacitive gas sensing element. Capacitive gas sensors operate based on changes in the dielectric properties of a material upon gas adsorption, which alters the capacitance of the sensor [20]. Materials like polymers or metal-organic frameworks (MOFs) can be used as the dielectric layer in capacitive sensors, and their interaction with polar gas molecules or changes in humidity can lead to measurable capacitance changes [17, 20].

The TENG provides the electrical energy to charge the capacitive sensor and measure capacitance change. This can be achieved by integrating the TENG with circuitry that converts the TENG's output into a suitable signal for capacitance measurement. This mechanism is particularly relevant for detecting gases that significantly influence the dielectric constant of the sensing material, such as humidity [20, 21]. A TENG-based system has been developed for selfpowered humidity sensing using a composite film [21].

Gas Ionization/Discharge Effects

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135









This less common but intriguing mechanism leverages the high voltage that can be generated by a TENG, particularly in certain configurations or under specific mechanical excitation. In the presence of certain gases, this high voltage can induce gas ionization or electrical discharge phenomena [23]. The characteristics of this ionization or discharge (e.g., breakdown voltage, current pulses) are dependent on the composition and concentration of the surrounding gas.

The sensing signal is derived from detecting electrical changes in these discharge characteristics. This mechanism has been explored for sensing inert gases, where the TENG's output can ionize the gas, and the resulting current is measured [23]. This approach is distinct in that the gas itself participates in an electrical process driven by the TENG's high voltage output. It may be particularly suitable for detecting gases that are easily ionizable.

DISCUSSION

The comparative analysis of sensing mechanisms TENG-based self-powered gas sensors highlights the versatility of TENG technology in this application. Each mechanism offers unique advantages and is suited for different types of gas sensing tasks.

Direct triboelectric property modulation provides a compact and potentially simpler device architecture by integrating sensing directly into the energy harvesting component. This mechanism is particularly sensitive to gases

that strongly interact with the surface chemistry and electronic properties of the triboelectric materials. However, achieving high selectivity for a specific gas using this mechanism alone can be challenging, as multiple gases might interact with the triboelectric surfaces. Material selection and surface functionalization are critical for tuning the sensitivity and selectivity [31, 37, 38].

TENG-driven resistive and capacitive sensing mechanisms offer the advantage of utilizing wellestablished and highly sensitive sensing materials and principles. This allows for leveraging existing knowledge and optimizing the sensing layer independently of the TENG's energy harvesting function. The TENG effectively replaces the need for an external power supply, enabling selfpowered operation. The challenge lies in efficiently converting the TENG's output into a stable power source for the sensing circuit and integrating the two components effectively. This hybrid approach can potentially offer better selectivity by choosing sensing materials specific to the target gas [9, 20].

The gas ionization/discharge mechanism is a less explored but potentially powerful approach, particularly for gases that are difficult to detect by other means. The high voltage capability of TENGs is uniquely leveraged here. However, controlling and reliably measuring the discharge phenomena can be complex, and the sensitivity and selectivity of this mechanism for a wide range of gases require further investigation [23].

Overall, the choice of sensing mechanism depends specific application requirements, on

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135









including the target gas, desired sensitivity and selectivity, operating environment, and cost constraints. Future research should focus on improving the sensitivity and selectivity of all these mechanisms. This can involve developing novel triboelectric materials with tailored gas

interactions, integrating highly selective sensing layers with TENGs, and optimizing the design of TENGs to enhance their output characteristics for sensing purposes [37, 38, 39, 40].



Advances in triboelectric nanogenerators in acoustics: Energy harvesting and Sound sensing

Furthermore, the development of TENG-based sensor arrays, combining multiple sensing elements or mechanisms, could lead to electronic nose-like devices capable of detecting and identifying complex gas mixtures [41]. The

integration of TENG-based gas sensors into wearable platforms and IoT networks is another promising direction, enabling continuous and distributed environmental monitoring personal healthcare applications [24, 25, 34, 102].

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135









Addressing challenges related to long-term stability, response time, and recovery time for different gases is also crucial for practical implementation.

Conclusion

In conclusion, TENGs offer a compelling pathway towards the development of self-powered gas sensors with diverse sensing mechanisms. Continued research into material science, device design, and integration strategies will be key to unlocking the full potential of TENG-based gas sensing for a wide range of applications, contributing to a healthier and safer environment.

REFERENCES

Nguyen H, El-Safty SA (2011) Meso- and macroporous Co3 O4 nanorods for effective VOC gas sensors. J Phys Chem C 115:8466-8474. https://doi.org/10.1021/jp1116189

Cohen AJ, Brauer M, Burnett R, Anderson HR, Frostad J, Estep K, Balakrishnan K, Brunekreef B, Dandona L, Dandona R (2017) Estimates and 25year trends of the global burden of disease attributable to ambient air pollution: an analysis of data from the Global Burden of Diseases Study 2015. Lancet 389:1907-1918

Tai H, Wang S, Duan Z, Jiang Y (2020) Evolution of breath analysis based on humidity and gas sensors: potential and challenges. Sens Actuators B Chem 318:128104

Peng X, Liu J, Tan Y, Mo R, Zhang Y (2022) A CuO thin film type sensor via inkjet printing technology with high reproducibility for ppblevel formaldehyde detection. Sens Actuators B Chem 362:131775

Kohse-Höinghaus K (2023)Combustion, chemistry, and carbon neutrality. Chem Rev 123:5139-5219.

https://doi.org/10.1021/acs.chemrev.2c00828

Wang S, Xie G, Tai H, Su Y, Yang B, Zhang Q, Du X, Jiang Y (2018) Ultrasensitive flexible selfpowered ammonia sensor based on triboelectric nanogenerator at room temperature. Nano Energy 51:231-240

Majhi SM, Mirzaei A, Kim HW, Kim SS, Kim TW (2021) Recent advances in energy-saving chemiresistive gas sensors: a review. Nano Energy 79:105369

Andre RS, Mercante LA, Facure MHM, Sanfelice RC, Fugikawa-Santos L, Swager TM, Correa DS (2022) Recent progress in amine gas sensors for food quality monitoring: novel architectures for sensing materials and systems. ACS Sens 7:2104– 2131.

https://doi.org/10.1021/acssensors.2c00639

He S, Gui Y, Wang Y, Cao L, He G, Tang C (2024) CuO/TiO2 /MXene-based sensor and SMS-TENG array integrated inspection robots for selfpowered ethanol detection and alarm at room temperature. ACS Sens 9:1188-1198. https://doi.org/10.1021/acssensors.3c01963

VOLUME 05 ISSUE 08 Pages: 1-9

OCLC - 1368736135









Shanmugasundaram A, Munirathinam K, Lee D-W Sn02 nanostructure-based acetone (2024)sensors for breath analysis. Micro Nano Syst Lett https://doi.org/10.1186/s40486-023-00196-5

Patial P, Deshwal M (2021) Systematic review on design and development of efficient semiconductor based surface acoustic wave gas sensor. Trans Electr Electron Mater 22:385-393. https://doi.org/10.1007/s42341-021-00332-1

Bogue R (2015) Detecting gases with light: a review of optical gas sensor technologies. Sens Rev 35:133-140

Van Cat V, Dinh NX, Phan VN, Le AT, Nam MH, Lam VD, Van Dang T, Van Quy N (2020) Realization of graphene oxide nanosheets as a potential masstype gas sensor for detecting NO2, SO2, CO, and NH3. Mater Today Commun 25:101682

Mirzaei A, Kordrostami Z, Shahbaz M, Kim J-Y, Kim HW, Kim SS (2022) Resistive-based gas sensors using quantum dots: a review. Sensors 22:4369. https://doi.org/10.3390/s22124369

Hu J, Ma H, Zhou Y, Ma L, Zhao S, Shi S, Li J, Chang Y (2023) Gas-sensing properties and mechanisms of 3D networks composed of ZnO tetrapod micronano structures at room temperature. Materials 17:203. https://doi.org/10.3390/ma17010203